

# Technical Data

## MATERIALS

### Carbon Steel

Channels made from high-quality carbon steel are continuously roll formed to precise dimensions. By cold working the steel mechanical properties are increased, allowing lightweight structures to carry the required load. Corrosion resistance of carbon steel varies widely with coating and alloy. See "Finishes" for more detailed information.

### Stainless Steel

Stainless steel channel is available in AISI Type 304 or 316 material. Both are non-magnetic and belong to the austenitic stainless steels group, based on alloy content and crystallographic structure. Like carbon steel, stainless steel exhibits increased strength when cold worked by roll-forming.

Several conditions make the use of stainless steel ideal. These include reducing long term maintenance costs, high ambient temperatures, appearance, and stable structural properties such as yield strength, and high creep strength.

Type 304 resists most organic chemicals, dyestuffs and a wide variety of inorganic chemicals at elevated or cryogenic temperatures. Type 316 contains slightly more nickel and adds molybdenum to give it better corrosion resistance in chloride and sulfuric acid environments. For more information concerning the differences between types 304 and 316, visit [www.cooperblinc.com/contactus](http://www.cooperblinc.com/contactus).

### Aluminum

Standard aluminum channel is extruded from aluminum alloy 6063-T6. Strut fittings are made from aluminum alloy 5052-H32.

The high strength to weight ratio of channel made of aluminum helps greatly reduce the overall cost of installation through ease of handling and field cutting.

Aluminum owes its excellent corrosion resistance to its ability to form an aluminum oxide film that immediately reforms when scratched or cut. In most outdoor applications, aluminum has excellent resistance to "weathering". The resistance to chemicals, indoor or outdoor, can best be determined by tests conducted by the user with exposure to the specific conditions for which it is intended. The corrosion resistance of aluminum to some commonly known chemicals is shown in the Corrosion Chart. For further information, contact us or the Aluminum Association.

### Fiberglass

We offer two fire retardant (FR) resins for strut systems, polyester and vinyl ester. Both resins are ideal for corrosive environments or nonconductive applications with moderate strength requirements. Some common types of environments where Vinyl Ester Resins are recommended, that Poly Esters are not, are paper mills, most any metal plating operation and any condition with


concentrated levels of Chlorine, [Cl<sup>-</sup>]. Please consult our fiberglass corrosion resistance charts on pg. 183 for specific chemical recommendation data.

Unlike other base materials depicted in this catalog, fiberglass exhibits unique physical property changes when operating in elevated temperature conditions that are a fraction of increase compared to steel or aluminum. Thus, it is advised against using fiberglass in temperatures greater than 200° F.

Please refer to the "Corrosion Resistance Guide" below for specific applications.

The fiberglass strut systems are manufactured from glass fiber-reinforced plastic shapes that meet ASTM E-84, Class 1 Flame Rating and self-extinguishing requirements of ASTM D-635. A surface veil is applied during pultrusion to insure a resin-rich surface and ultraviolet resistance.

While polyester is sufficient for most uses, vinyl ester is suitable for a broader range of environments.



#### B-Line Steel Strut is stamped with:


- Traceable to the steel's origin
- Material/Finish
- B-Line part number designation
- Company Name

## FINISHES

### Zinc Coatings

Zinc protects steel in two ways. First it protects the steel as a coating and second as a sacrificial anode to repair bare areas such as cut edges, scratches, and gouges. The corrosion protection of zinc is directly related to its thickness and the environment. This means a .2 mil coating will last twice as long as a .1 mil coating in the same environment.

Galvanizing also protects cut and drilled edges.



### Electrogalvanized Zinc

Electrogalvanized Zinc (also known as zinc plated or electroplated) is the process by which a coating of zinc is deposited on the steel by electrolysis from a bath of zinc salts.

A rating of SC3, our standard, provides a minimum zinc coating thickness of .5 mils (excluding hardware, which is SC1 = .2 mils).

When exposed to air and moisture, zinc forms a tough, adherent, protective film consisting of a mixture of zinc oxides, hydroxides, and carbonates. This film is in itself a barrier coating which slows subsequent corrosive attack on the zinc. This coating is usually recommended for indoor use in relatively dry areas, as it provides ninety-six hours protection in salt spray testing per ASTM B117.

### Chromium/ Zinc

Chromium/ Zinc is a corrosion resistant composition, which was developed to protect fasteners and small bulk items for automotive use. The coating applications have since been extended to larger parts and other markets.

Chromium/Zinc composition is an aqueous coating dispersion containing chromium, proprietary organics, and zinc flake.

This finish provides 500 hours protection in salt spray testing per ASTM B117.

### Pre-Galvanized Zinc

(Mill galvanized, hot dip mill galvanized or continuous hot dip galvanized) Pre-galvanized steel is produced by coating coils of sheet steel with zinc by continuously rolling the material through molten zinc at the mills. This is also known as mill galvanized or hot dip mill galvanized. These coils are then slit to size and fabricated by roll forming, shearing, punching, or forming to produce our pre-galvanized strut products.

The G90 specification calls for a coating of .90 ounces of zinc per square foot of steel. This results in a coating of .45 ounces per square foot on each side of the sheet. This is important when comparing this finish to hot dip galvanized after fabrication.

During fabrication, cut edges and welded areas are not normally zinc coated; however, the zinc near the uncoated metal becomes a sacrificial anode to protect the bare areas after a short period of time.

### Hot Dip Galvanized After Fabrication (Hot dip galvanized or batch hot dip galvanized)

Hot dip galvanized strut products are fabricated from steel and then completely immersed in a bath of molten zinc. A metallic bond occurs resulting in a zinc coating that completely coats all surfaces, including edges and welds.


Another advantage of this method is coating thickness. Strut products that are hot dip galvanized after fabrication have a minimum thickness of 1.50 ounces per square foot on each side, or a total 3.0 ounces per square foot of steel, according to ASTM A123.

The zinc thickness is controlled by the amount of time each part is immersed in the molten zinc bath as well as the speed at which it is removed. The term "double dipping" refers to parts too large to fit into the galvanizing kettle and, therefore, must be dipped one end at a time. It does not refer to extra coating thickness.

The layer of zinc which bonds to steel provides a dual protection against corrosion. It protects first as an overall barrier coating. If this coating happens to be scratched or gouged, zinc's secondary defense is called upon to protect the steel by galvanic action.

Hot-Dip Galvanized After Fabrication is recommended for prolonged outdoor exposure and will usually protect steel for 20 years or more in most atmospheric environments and in many industrial environments. For best results, a zinc rich paint (available from B-Line) should be applied to field cuts. The zinc rich paint will provide immediate protection for these areas and eliminate the short time period for galvanic action to "heal" the damaged coating.

Anticipated Life of Zinc Coatings In Various Atmospheric Environments



# Technical Data

## DURA-GREEN™ and DURA-COPPER™ Epoxy Coatings

DURA-GREEN and DURA-COPPER epoxy coatings are water borne epoxy coatings applied to B-Line products by a precisely controlled cathodic electro-deposition process. This process is accomplished using a conveyor to transport channel and fittings through several cleaning, phosphatizing and application stages prior to being baked (See diagram below).

This custom-designed paint system is used for painting all channels, channel combinations, slotted angle, and fittings.

Samples are selected on a routine basis for Salt Spray (fog) testing to verify the quality of the finish. These tests are performed in accordance with ASTM B117 and evaluated and related according to ASTM D1654 (Tables 1 & 2).

The DURA-GREEN and DURA-COPPER Epoxy coatings have been tested and listed by Underwriters Laboratories in accordance with "Standard for Surface Metal Raceway and Fittings, UL5" and

"Standard for Pipe Hanger Equipment for Fire Protection Service, UL203".

Due to DURA-GREEN's organically based composition, it seats itself into porous surfaces more completely and efficiently than zinc coatings. As these porous caverns are filled along the material profile, the outer finished surface demonstrates an increased smooth uniform plane which produces considerably less off-gasing when tested.

DURA-GREEN channel meets or exceeds 100 level clean room standards. This was confirmed by testing the channel in accordance with Boeing (PCL) Standards, which are more stringent and complete than ASTM E595-93. DURA-GREEN was found to be a superior finish, due in part to its proven application process.

### PVC Coating

Another of the corrosion resistant coatings offered by B-Line is PVC (polyvinyl chloride), applied over steel or aluminum channel and fittings. The PVC coating process begins by cleaning the product

thoroughly. A bonding coat is applied to the part and then preheated to a temperature above the melting point of the coating powder. The product is then passed through a fluidized bed of vinyl plastic powder where the powder particles melt, adhere and flow out to form a smooth continuous coating. The thickness is controlled by the base metal temperature and the immersion time in the bed. It is then post-heated to complete the fusion of the outer surfaces.

The standard coating thickness of B-Line's PVC coated products is 15 mils (.380 mm), plus or minus 5 mils (.125 mm). Since the chemistry, not the thickness of vinyl plastic PVC determines longevity, a coating of 10 to 20 mils (.250 to .500 mm) is more than adequate. If the corrosive conditions are such that the plasticizers are leached out, a thicker coating will do little to extend the life of a coated product.

For certain environments, a plastisol dipped PVC coating is available on request.

PVC coating depends totally on the concept of encapsulation attached to the base metal by a bonding agent. If any hole or discontinuity occurs, the corrosive action can undercut the base metal to a point where all that remains is the PVC.


In the event of field cuts or any other damage to the coating, a liquid PVC patch, available from B-Line, must be applied to maintain the integrity of the coating. After the installation is complete, a thorough inspection should be performed to assure the absence of voids, pinholes, or cuts.

## SALT SPRAY TEST RESULTS

| Type of Finish             | Unscribed 5% Failure (1) | Scribed 1/8" (3.2) Creepage from Scribe (1) |
|----------------------------|--------------------------|---------------------------------------------|
| B-Line DURA-GREEN Epoxy    | 1000 Hours               | 312 Hours                                   |
| Mill Galv. (Pre-Galv.) G90 | 192 Hours                | 288 Hours                                   |
| Perma-Green                | 438 Hours                | 231 Hours                                   |
| Zinc Chromate              | 36 Hours                 | 96 Hours                                    |
| Industry Green (Range)     | 10 to 36 Hours           | 4 to 30 Hours                               |





(1) All salt spray (fog) tests conducted in accordance with ASTM B117 and evaluated and rated according to ASTM D1654 Tables 1 & 2. Tests are performed and certified by an independent testing laboratory.

## DURA-GREEN™/DURA-COPPER™ EPOXY COATING PROCESS



## SELECTION CHART

for Channels, Materials and Hole Patterns

| Channel Type | Channel Dimensions                                                                |        |                                                                                   |        | Material & Thickness * |          |          |          | Channel Hole Pattern **                                                            |                                                                                     |                                                                                     |                                                                                     |                                                                                     |
|--------------|-----------------------------------------------------------------------------------|--------|-----------------------------------------------------------------------------------|--------|------------------------|----------|----------|----------|------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|
|              | Height                                                                            |        | Width                                                                             |        | Stainless Steel        |          |          |          | SH                                                                                 | S                                                                                   | H17/8                                                                               | TH                                                                                  | KO6                                                                                 |
|              |  | (mm)   |  | (mm)   | Steel                  | Alum.    | Type 304 | Type 316 |  |  |  |  |  |
|              |                                                                                   |        |                                                                                   |        | <u>1</u>               | <u>2</u> | <u>3</u> | <u>4</u> |                                                                                    |                                                                                     |                                                                                     |                                                                                     |                                                                                     |
| <b>B11</b>   | 3 1/4"                                                                            | (82.5) | 1 5/8"                                                                            | (41.3) | 12 Ga.                 | .105     | –        | –        | <u>1</u>                                                                           | <u>1</u>                                                                            | <u>1</u>                                                                            | –                                                                                   | <u>1</u>                                                                            |
| <b>B12</b>   | 2 7/16"                                                                           | (61.9) | 1 5/8"                                                                            | (41.3) | 12 Ga.                 | .105     | –        | –        | <u>1 2</u>                                                                         | <u>1</u>                                                                            | <u>1 2</u>                                                                          | –                                                                                   | <u>1 2</u>                                                                          |
| <b>B22</b>   | 1 5/8"                                                                            | (41.3) | 1 5/8"                                                                            | (41.3) | 12 Ga.                 | .105     | 12 Ga.   | 12 Ga.   | <u>1 2 3 4</u>                                                                     | <u>1 3</u>                                                                          | <u>1 2 3</u>                                                                        | <u>1</u>                                                                            | <u>1 2</u>                                                                          |
| <b>B24</b>   | 1 5/8"                                                                            | (41.3) | 1 5/8"                                                                            | (41.3) | 14 Ga.                 | .080     | 14 Ga.   | 14 Ga.   | <u>1 2 3 4</u>                                                                     | <u>1</u>                                                                            | <u>1 2 3</u>                                                                        | –                                                                                   | <u>1 2</u>                                                                          |
| <b>B26</b>   | 1 5/8"                                                                            | (41.3) | 1 5/8"                                                                            | (41.3) | 16 Ga.                 | –        | –        | –        | <u>1</u>                                                                           | <u>1</u>                                                                            | <u>1</u>                                                                            | –                                                                                   | <u>1</u>                                                                            |
| <b>B32</b>   | 1 3/8"                                                                            | (34.9) | 1 5/8"                                                                            | (41.3) | 12 Ga.                 | –        | 12 Ga.   | –        | <u>1 3</u>                                                                         | <u>1</u>                                                                            | <u>1 3</u>                                                                          | –                                                                                   | <u>1</u>                                                                            |
| <b>B42</b>   | 1"                                                                                | (25.4) | 1 5/8"                                                                            | (41.3) | 12 Ga.                 | –        | 12 Ga.   | –        | <u>1 3</u>                                                                         | <u>1</u>                                                                            | <u>1 3</u>                                                                          | –                                                                                   | <u>1</u>                                                                            |
| <b>B52</b>   | 1 3/16"                                                                           | (20.6) | 1 5/8"                                                                            | (41.3) | 12 Ga.                 | –        | 12 Ga.   | 12 Ga.   | <u>1 3 4</u>                                                                       | <u>1</u>                                                                            | <u>1</u>                                                                            | –                                                                                   | <u>1</u>                                                                            |
| <b>B54</b>   | 1 3/16"                                                                           | (20.6) | 1 5/8"                                                                            | (41.3) | 14 Ga.                 | .080     | 14 Ga.   | 14 Ga.   | <u>1 2 3 4</u>                                                                     | <u>1</u>                                                                            | <u>1 2 3 4</u>                                                                      | –                                                                                   | <u>1 2</u>                                                                          |
| <b>B56</b>   | 1 3/16"                                                                           | (20.6) | 1 5/8"                                                                            | (41.3) | 16 Ga.                 | –        | –        | –        | <u>1</u>                                                                           | <u>1</u>                                                                            | <u>1</u>                                                                            | –                                                                                   | <u>1</u>                                                                            |
| <b>B62</b>   | 1 3/16"                                                                           | (20.6) | 1 3/16"                                                                           | (20.6) | 18 Ga.                 | –        | –        | –        | –                                                                                  | –                                                                                   | –                                                                                   | –                                                                                   | –                                                                                   |
| <b>B72</b>   | 1 3/32"                                                                           | (10.3) | 1 3/16"                                                                           | (20.6) | 18 Ga.                 | –        | –        | –        | –                                                                                  | –                                                                                   | –                                                                                   | –                                                                                   | –                                                                                   |

The selection has been prepared to provide a reference for available channel, materials and hole patterns. Material types available for various hole patterns are defined by numbers 1 thru 4.

Some stainless steel channels with hole patterns are available on special order only.

\*Metric equivalent for thicknesses shown in chart.

12 Ga. = 2.6 mm

14 Ga. = 1.9 mm

16 Ga. = 1.5 mm

18 Ga. = 1.2 mm

.105 = 2.6 mm

.080 = 2.0 mm

\*\*1 - Steel

2 - Aluminum

3 - Type 304 Stainless Steel

4 - Type 316 Stainless Steel

Properties may vary due to commercial tolerances of the material.



| Channel Part Numbering  |                                   |        |                 |
|-------------------------|-----------------------------------|--------|-----------------|
| Example:                |                                   |        |                 |
| <b>B22 SH - 120 SS4</b> |                                   |        |                 |
| Channel Type            | Hole Patterns                     | Length | Material/Finish |
| B11                     | SH (pg. 40)                       | 120    | GRN             |
| B12                     | S (pg. 40)                        | 240    | GLV             |
| B22 †                   | H178 (pg. 40)                     |        | HDG             |
| B24 †                   | TH (pg. 41)                       |        | YZN             |
| B26                     | K06 (pg. 41)                      |        | SS4             |
| B32                     | SHA (pg. 41)                      |        | SS6             |
| B42                     | S58 (pg. 42)                      |        | AL              |
| B52 †                   | M (pg. 42)                        |        |                 |
| B54 †                   | H25 (pg. 43)                      |        |                 |
| B56                     | H112 † (pg. 42)                   |        |                 |
| B62                     | * Leave blank for no hole pattern |        |                 |
| B72                     |                                   |        |                 |

Reference page 14 for general fitting and standard finish specifications.

# B52 Channel & Combinations

## B52


- Thickness: 12 Gauge (2.6 mm)
- Standard lengths: 10' (3.05 m) & 20' (6.09 m)
- Standard finishes: Plain, DURA-GREEN™, Pre-Galvanized, Stainless Steel Type 304 or 316, Hot-Dipped Galvanized
- Weight: 1.27 Lbs./Ft. (1.89 kg/m)



## SECTION PROPERTIES


| Channel     | Weight   |        | Areas of Section |                 | Moment of Inertia (I) |                 | Section Modulus (S) |                 | Radius of Gyration (r) |        | Moment of Inertia (I) |                 | Section Modulus (S) |                 | Radius of Gyration (r) |        |
|-------------|----------|--------|------------------|-----------------|-----------------------|-----------------|---------------------|-----------------|------------------------|--------|-----------------------|-----------------|---------------------|-----------------|------------------------|--------|
|             |          |        |                  |                 |                       |                 |                     |                 |                        |        |                       |                 |                     |                 |                        |        |
|             | lbs./ft. | kg/m   | sq. in.          | cm <sup>2</sup> | in. <sup>4</sup>      | cm <sup>4</sup> | in. <sup>3</sup>    | cm <sup>3</sup> | in.                    | cm     | in. <sup>4</sup>      | cm <sup>4</sup> | in. <sup>3</sup>    | cm <sup>3</sup> | in.                    | cm     |
| <b>B52</b>  | 1.313    | (1.95) | .386             | (2.49)          | .0320                 | (1.33)          | .0673               | (1.10)          | .288                   | (.73)  | .1404                 | (5.84)          | .1728               | (2.83)          | .603                   | (1.53) |
| <b>B52A</b> | 2.627    | (3.91) | .773             | (4.99)          | .1517                 | (6.31)          | .1868               | (3.06)          | .443                   | (1.13) | .2809                 | (11.69)         | .3457               | (5.67)          | .603                   | (1.53) |

Calculations of section properties are based on metal thicknesses as determined by the AISI Cold-Formed Steel Design Manual.




### B52A

Wt. 2.54 Lbs./Ft. (3.78 kg/m)



### B52B3

Wt. 3.81 Lbs./Ft. (5.67 kg/m)





### B52B4

Wt. 5.08 Lbs./Ft. (7.56 kg/m)

# B54 Channel & Combinations

## B54


- Thickness: 14 Gauge (1.9 mm)
- Standard lengths: 10' (3.05 m) & 20' (6.09 m)
- Standard finishes: Plain, DURA-GREEN™, Pre-Galvanized, Hot-Dipped Galvanized, Stainless Steel Type 304 or 316, Aluminum
- Weight: .97 Lbs./Ft. (1.44 kg/m)



## SECTION PROPERTIES


| SECTION PROPERTIES |          |        |                  |                 | X - X Axis            |                 |                     |                 |                        |        | Y - Y Axis            |                 |                     |                 |                        |        |
|--------------------|----------|--------|------------------|-----------------|-----------------------|-----------------|---------------------|-----------------|------------------------|--------|-----------------------|-----------------|---------------------|-----------------|------------------------|--------|
| Channel            | Weight   |        | Areas of Section |                 | Moment of Inertia (I) |                 | Section Modulus (S) |                 | Radius of Gyration (r) |        | Moment of Inertia (I) |                 | Section Modulus (S) |                 | Radius of Gyration (r) |        |
|                    | lbs./ft. | kg/m   | sq. in.          | cm <sup>2</sup> | in. <sup>4</sup>      | cm <sup>4</sup> | in. <sup>3</sup>    | cm <sup>3</sup> | in.                    | cm     | in. <sup>4</sup>      | cm <sup>4</sup> | in. <sup>3</sup>    | cm <sup>3</sup> | in.                    | cm     |
| B54                | 1.016    | (1.51) | .299             | (1.93)          | .0263                 | (1.09)          | .0560               | (.92)           | .297                   | (.75)  | .1106                 | (4.60)          | .1361               | (2.23)          | .608                   | (1.55) |
| B54A               | 2.032    | (3.02) | .598             | (3.86)          | .1226                 | (5.10)          | .1510               | (2.47)          | .453                   | (1.15) | .2212                 | (9.12)          | .2722               | (4.46)          | .608                   | (1.55) |

Calculations of section properties are based on metal thicknesses as determined by the AISI Cold-Formed Steel Design Manual.




### B54A

Wt. 1.94 Lbs./Ft. (2.89 kg/m)



### B54B3

Wt. 2.91 Lbs./Ft. (4.33 kg/m)





### B54B4

Wt. 3.88 Lbs./Ft. (5.77 kg/m)

# B56 Channel & Combinations

## B56


- Thickness: 16 Gauge (1.5 mm)
- Standard lengths: 10' (3.05 m) & 20' (6.09 m)
- Standard finishes: Plain, DURA-GREEN™, Pre-Galvanized, Hot-Dipped Galvanized
- Weight: .85 Lbs./Ft. (1.26 kg/m)



## SECTION PROPERTIES


| SECTION PROPERTIES |          |        |                  |                 | X - X Axis            |                 |                     |                 |                        |        | Y - Y Axis            |                 |                     |                 |                        |        |
|--------------------|----------|--------|------------------|-----------------|-----------------------|-----------------|---------------------|-----------------|------------------------|--------|-----------------------|-----------------|---------------------|-----------------|------------------------|--------|
| Channel            | Weight   |        | Areas of Section |                 | Moment of Inertia (I) |                 | Section Modulus (S) |                 | Radius of Gyration (r) |        | Moment of Inertia (I) |                 | Section Modulus (S) |                 | Radius of Gyration (r) |        |
|                    | lbs./ft. | kg/m   | sq. in.          | cm <sup>2</sup> | in. <sup>4</sup>      | cm <sup>4</sup> | in. <sup>3</sup>    | cm <sup>3</sup> | in.                    | cm     | in. <sup>4</sup>      | cm <sup>4</sup> | in. <sup>3</sup>    | cm <sup>3</sup> | in.                    | cm     |
| B56                | .894     | (1.33) | .263             | (1.70)          | .0241                 | (1.00)          | .0546               | (.89)           | .303                   | (.77)  | .0966                 | (4.02)          | .1189               | (1.95)          | .606                   | (1.54) |
| B56A               | 1.789    | (2.66) | .526             | (3.39)          | .1205                 | (5.02)          | .1484               | (2.43)          | .479                   | (1.22) | .1931                 | (8.04)          | .2377               | (3.89)          | .606                   | (1.54) |

Calculations of section properties are based on metal thicknesses as determined by the AISI Cold-Formed Steel Design Manual.




### B56A

Wt. 1.70 Lbs./Ft. (2.53 kg/m)



### B56B3

Wt. 2.55 Lbs./Ft. (3.79 kg/m)



### B56B4


Wt. 3.40 Lbs./Ft. (5.06 kg/m)

# Fittings

This section offers a full selection of fittings and accessories to complete our strut system. Fittings are made from hot rolled, pickled and oiled plate or strip steel in accordance with ASTM A1018 33,000 PSI min. yield, unless noted.

## Dimensions

The following dimensions apply to all fittings except as noted:



## Materials & Finishes (Unless otherwise noted)

| Finish Code | Finish                   | Specification                          |
|-------------|--------------------------|----------------------------------------|
| PLN         | Plain                    | ASTM A1018<br>33,000 PSI min. yield    |
| ZN          | Electro-Plated Zinc      | ASTM B633 SC3 Type III<br>or ASTM A653 |
| GRN         | DURA-GREEN™              |                                        |
| HDG         | Hot-Dipped Galvanized    | ASTM A123                              |
| SS4         | Stainless Steel Type 304 | ASTM A240                              |
| SS6         | Stainless Steel Type 316 | ASTM A240                              |
| AL          | Aluminum                 | ASTM B209                              |

Note: A minimum order may apply on special material and finishes.

## Load Data

The load data published includes safety factor of 2.5 when used with 12 ga. (2.6) channel (safety factor = ratio of ultimate load to the design load).

Use  $\frac{1}{2}$ "-13 x  $\frac{7}{8}$ " hex head cap screws and  $\frac{1}{2}$ "-13 (N225 or TN225) channel nuts for the rated results.

## Recommended Bolt Torque

| Bolt Size | $\frac{1}{4}$ "-20 | $\frac{5}{16}$ "-18 | $\frac{3}{8}$ "-16 | $\frac{1}{2}$ "-13 |
|-----------|--------------------|---------------------|--------------------|--------------------|
| Foot/Lbs. | 6                  | 11                  | 19                 | 50                 |
| Nm        | 8                  | 15                  | 26                 | 68                 |

See chart on page 112 for setscrew torque.

## Hardware

Nuts and bolts are not included with the fittings and must be ordered separately, unless noted.

## Pre-Assembled Fittings

Some fittings are available with hex head cap screws and channel nuts pre-assembled. These fittings and finishes will be flagged using the following symbol.



## Metric


Metric dimensions are shown in parentheses. Unless noted, all metric dimensions are in millimeters.



## B823 PROFILE END CAPS

- Material: PVC
- Available in colors: White (W), Yellow (Y), Black (BLK), Gray (GRY), Green (GRN)


Approx.  $\frac{3}{4}$ " deep  
(19.0)



| Part No.        | Fits<br>Channel Sizes | Wt./C |       |
|-----------------|-----------------------|-------|-------|
|                 |                       | Lbs.  | kg    |
| <b>B823-22A</b> | B22A, B24A, B26A      | 6.9   | (3.1) |
| <b>B823-22</b>  | B22, B24, B26         | 4.1   | (1.8) |
| <b>B823-42</b>  | B42                   | 3.8   | (1.7) |
| <b>B823-52</b>  | B52, B54, B56         | 3.5   | (1.6) |

## B825 PLASTIC END CAPS


- Material: Polyurethane
- Available in colors: Gray (GRY), Green (GRN)



| Part No.       | Fits<br>Channel Sizes | Wt./C |       |
|----------------|-----------------------|-------|-------|
|                |                       | Lbs.  | kg    |
| <b>B825-22</b> | B22 & B24             | 2.0   | (0.9) |
| <b>B825-52</b> | B52 & B54             | 1.0   | (0.4) |

## B408SLBVNS Series STAND-OFF BRACKETS

- Material:  $\frac{1}{4}$ " (6.3)
- Standard Finishes: HDG, ZN, GRN
- For pipe or rigid conduit sizes of  $1\frac{1}{2}$ " (32) and 2" (50) use with B501 Series 'U'-Bolts
- For strut channels  $1\frac{5}{8}$ " (41.3) wide use with B500 Series Square 'U'-Bolts
- Hardware is not included



| Part No.           | A                |        | Wt./C |         |
|--------------------|------------------|--------|-------|---------|
|                    | In.              | (mm)   | Lbs.  | kg      |
| <b>B408SLBVNS</b>  | $3\frac{1}{2}$ " | (88.9) | 189   | (85.7)  |
| <b>B408SLBVNS1</b> | 3"               | (76.2) | 220   | (99.8)  |
| <b>B408SLBVNS2</b> | 2"               | (50.8) | 236   | (107.0) |

